



Polypropylene (PP)

# BURPOLEN 1005 T40 BLACK

## Product Description

BURPOLEN 1005 T40 BLACK is a %40 mineral modified polypropylene.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	1,22 - 1,28
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	7 - 13
Ash Content	%	ISO 3451	38 - 43

## Mechanical properties

Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	20 - 35
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	≥ 8
Flexural modulus (2mm/min) (23°C)	MPa	ISO 178	2600 - 3600

## Impact

Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 2
----------------------------	-------------------	---------	-----

## Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

## Processing Techniques

BURPOLEN 1005 T40 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

## Storage

The BURPOLEN® 1005 T40 BLACK in pellet form is packed in bigbag (1000 Kg).