



Polypropylene (PP)

BURPOLEN 2203 T2 AS6 BLACK

Product Description

BURPOLEN 2203 T2 AS6 BLACK is a %20 mineral modified polypropylene.

Properties	Unit	Test Method	Value
Physical properties			
Density, (23 °C)	g/cm ³	ISO 1183	1.03 - 1.08
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	9 - 15
Ash Content	%	ISO 3451	18 - 22
Mechanical properties			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	30 - 38
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	≥ 5
Flexural modulus (2mm/min) (23°C)	MPa	ISO 178	2800 – 3300
Flexural Strength (2mm/min) (23°C)	MPa	ISO 178	45 - 60
Impact			
Notched Izod Impact (23°C)	kJ/m ²	ISO 180	≥ 3

Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

Processing Techniques

BURPOLEN 2203 T2 AS6 is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

Storage

The BURPOLEN® 2203 T2 AS6 in pellet form is packed in bigbag (1000 Kg).