



Polypropylene (PP)

BURPOLEN C815T-FAT BLACK

Product Description

BURPOLEN C815-FAT BLACK is a reinforced homopolymer.

Properties	Unit	Test Method	Value
Physical properties			
Density, (23 °C)	g/cm ³	ISO 1183	0.90 – 0.96
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	7 - 14
Ash Content	%	ISO 3451	0 - 7
Mechanical properties			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	16 - 30
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	≥ 30
Tensile modulus (1mm/min) (23°C)	MPa	ISO 527	1200 - 1400
Impact			
Notched Izod Impact (23°C)	kJ/m ²	ISO 180	8 - 12

Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

Processing Techniques

BURPOLEN C815T-FAT BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

Storage

The BURPOLEN® C815T-FAT BLACK in pellet form is packed in bigbag (1000 Kg).