



Polypropylene (PP)

# BURPOLEN F0720 BLACK

## Product Description

BURPOLEN F0720 BLACK is a %20 mineral modified polypropylene.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	1.03 - 1.08
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	7 - 12
Ash Content	%	ISO 3451	19 - 23
<b>Mechanical properties</b>			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	20 - 30
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	20 - 35
Tensile modulus (1mm/min)	Mpa	ISO 527	1900 - 2500
<b>Impact</b>			
Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 4

## Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

## Processing Techniques

BURPOLEN F0720 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

## Storage

BURPOLEN® F0720 BLACK in pellet form is packed in bigbag (1000 Kg).